

100% Cotton Carded TFO Yarn (For SWEATER)

Test Parameter	20/2	30/2
Actual Count (Ne)	10.3	15.32
Count C.V.%	0.98	1.10
Strength C.V.%	2.55	2.65
CSP	2706	2750
RKM (gm/tex)	15.90	17.20
RKM C.V.%	6.38	6.50
Elongation %	4.25	4.10
Elongation C.V.%	5.20	7.40
U% & Imperfections		
Uster %	7.50	8.20
Thin (-50%) / km	0.00	0.00
Thick (+50) / km	4.00	7.00
Neps (+200%) / km	8.00	14.00
Total Imperfections / km	12.00	21.00
Hairiness	11.80	8.70
TPI	15.90	17.20